



Prime® Fibrabel®



Product class

Type L-MDF according to EN 622-5

Scope

High-quality low-density MDF for use in dry conditions and in particular for interior decoration and furniture production. Industrially coated on both sides with a white and even UV primer.

Upon request, this MDF board can be supplied with a PEFC, FSC or FSC Controlled Wood certificate.

Application

MDF Prime® Fibrabel® allows for an excellent paint finish while saving costs and time. After degreasing and (light) sanding the panel surface may be finished immediately in the desired colour – matt, silk or high gloss – using a solvent-based or water-based coating.

MDF Prime® Fibrabel® has a low level of formaldehyde emission (class E1); it is suitable for interior decoration and furniture applications and highly popular among DIY enthusiasts.

The two-sided, industrially applied white UV primer offers the following benefits:

- A smoother end result than with a manually applied primer, partly thanks to correct and controlled paint distribution
- The UV primer coating is cured using ultra-violet light, resulting in a more impact- and wear-resistant surface
- Excellent adhesion, even when using water-based coatings
- Correct colour rendering of the paint, therefore a perfectly coloured end result
- Cost and time savings: less paint consumption due to lower absorption; and less paint work required
- Easy finishing of joints and screws using fine fillers and intermediate sanding

Processing guidelines

General preparation of paintworks

Acclimatize the MDF boards prior to applying the finishing coating: place the panels in the area where they will be used and ensure that the level of humidity and the temperature match the circumstances of final use. This will help to prevent cracks and tension on the coated surface that may occur under highly fluctuating temperature or humidity.

Repair any damage (e.g. around visible crews in the surface) using materials that are compatible with the subsequent paint system, for instance polyester fillers.





Prime® Fibrabel®



Pre-treatment of panels

Degrease MDF Prime® Fibrabel® (e.g. using an ammonia solution or a traditional detergent); next, lightly sand the panel using relatively fine sandpaper (P180 to P320) and remove the sanding dust. Allow the surface to dry if necessary.

Finishing the panels

Finish MDF Prime® Fibrabel® as needed with a brush, roller or spray gun depending on the chosen paint. Make sure to respect the basic rules of paint finishing to avoid overlapping paint marks, droplets, etc. Also make sure to follow the processing instructions provided with the chosen coating system.

Apply at least two final coatings for the best finishing result. Lightly sand in between coatings preferably using sandpaper > P200.

Note: finishing with latex paint

The material allows for finishing with latex paint. Because latex paint is more demanding in terms of adhesion, we recommend that you use a highly moisture-resistant and suitable primer.

Finishing the edges

The edges of MDF Prime® Fibrabel® have a lower density than the surface and therefore will absorb paint more easily. The edges must be sanded thoroughly and filled – several times, if needed – with a suitable filling primer. After applying filling coatings to the edges the fibres may swell under humid conditions. Intermediate sanding is therefore necessary. There is a wide choice of filling primers and polyester fillings for the end grain of wooden sheet material available on the market.

General instructions

The MDF board must be applied in service class 1 (restrictions as regards temperature and ambient humidity) and may only be used in biological hazard class 1 of EN 335-3. The boards must be protected from any direct contact with water. They must be stacked flat, on a pallet or using a sufficient number of cross members. Any contact with the floor must be avoided. The board will expand or shrink under variable humidity conditions. Make sure to use suitable sawing, milling and drilling tools.





Prime® Fibrabel®



Dimensions and types

Standard thickness: 18 mm. Standard width: 1220 mm. Standard length: 2440 mm or 3050 mm. Other dimensions or thicknesses (12 to 40 mm) are available upon request. MDF Prime® Fibrabel® is also available in a version for application in dry conditions: MDF Prime® Fibrabel®.

For more information please contact our sales team or send an email to sales.spanolux@unilin.com.

Technical specifications

Property	Test method	Unit	Ranges of nominal thickness (mm)				
			> 6 to 9	> 9 to 12	> 12 to 19	> 19 to 30	> 30 to 45
Swelling in thickness 24 h	EN 317	%	20	16	14	12	11
Internal bond	EN 319	N/mm ²	0,45	0,45	0,45	0,45	0,40
Bending strength	EN 310	N/mm ²	20	20	18	15	14
Modulus of elasticity in bending	EN 310	N/mm ²	1700	1700	1600	1500	1400

Prime® Fibrabel®



Spanolux SPRL - Rue de la Forêt 2 - B-6690 Vielsalm
T +32 80 29 27 10 - F +32 80 29 27 23
sales.spanolux@unilin.com - TVA BE 0456 573 456

The data on this information sheet are based on internal testing and are purely informative and are provided according to Spanolux SPRL knowledge at the time it was issued. Nothing in this information sheet can be construed as a commitment of Spanolux SPRL, nor can it result in any liability whatsoever of Spanolux SPRL. The information provided is subject of change at any time without any prior notification. © Spanolux - all rights reserved

Issue date: 13/06/2016